




Formerly known as



JSR Corporation
www.jsr.co.jp

POLYBUTADIENE RUBBER-BR

GRADE	Product Stain	Cis Content (%)	Mooney Viscosity ML 1+4 (100°C)	Specific Gravity	Characteristics	Application
BR 01	NS	95	45	0.9	Excellent Processability Especially BR only Compound	Tires , belts , Hoses , Footwear , Rubberized , Cloth , Industrial Goods.
To 700	NS	95	42	0.9	Narrow Molecular Weight Distribution Compared With Br01	Tires , Belts
BR 51	NS	95	38	0.9	Low MV type of T0700. Excellent Processability.	Tires
BR 730	NS	95	55	0.9	High MV type of T0700. Excellent Abrasion Resistance & Rebound Resilience.	Tires, Sports Goods.



Performance
Materials
Pvt. Ltd.